



SAINT-ASTIER

LIME, LIFELONG EXCELLENCE

DÉCORCHAUX®

CALCIC LIME



DECORATION RANGE

CALCIC LIME

THE + BENEFITS

- ◆ EXTRA WHITE
- ◆ FAT AND EASY TO APPLY
- ◆ IDEAL FOR LIMEWASHES
- ◆ SANITISE THE SUPPORT

AREAS OF USE

- > Limewash
- > Finishing coat
- > Other uses : consult us

PACKAGING

- > **DÉCORCHAUX® LIME POWDER**
20 kg bag
50 bags per pallet (1 T pallet)
- > **DÉCORCHAUX® LIME PUTTY**
12 kg bucket
33 buckets per pallet (396 kg pallet)

PRODUCT COMPOSITION

Calcic lime in powder or putty form selected by Saint-Astier®.

SHELF LIFE & GUARANTEE

18 months from date of manufacture, protected from moisture and in unopened original packaging. Manufacturer civil liability.





PLASTER FINISHING COAT

	INTERIOR	INTERIOR AND EXTERIOR
	Scratch and coarse finishes	Trowel, floated, smoothed
LIME CONSUMPTION	1.5 to 1.8 kg / m ² for 8 mm thickness	0.9 to 1.1 kg / m ² for 5 mm thickness
LIME CONSUMPTION	3.2 to 4 kg / m ² for 8 mm thickness	1.9 to 2.4 kg / m ² for 5 mm thickness

FINISHED THICKNESS approx. 5 mm : as the strengths of these render are low, scraped, raised or brushed finishes may present a risk of permanent powdering.

LIMEWASH

LIME CONSUMPTION	100 to 300 g / m ² per coat depending on dilution
LIME CONSUMPTION	150 to 300 g / m ² per coat depending on dilution

*For diluting limewash, a Technical Implementation Document (DTMO limewash) is available on our website www.saint-astier.com. Please consult it before starting any work.

FURTHER INFORMATION

- Pigments can be used with this lime. Contact the technical manager for more information.



WEATHER CONDITIONS

Between 8° C and 30° C.
In hot weather, dampen surfaces the day before use. Apply and keep moist, spraying, plaster coatings, moderately, for 48 hours.

EQUIVALENCE

1 bag of DÉCORCHAUX® lime 20 Kg = 4 10 litres buckets

